

**Calcioandryobertsite****KCaCu<sub>5</sub>(AsO<sub>4</sub>)<sub>4</sub>[As(OH)<sub>2</sub>O<sub>2</sub>]<sub>2</sub>·2H<sub>2</sub>O**

**Crystal Data:** Monoclinic. *Point Group:* 2/m. Crystals have {100} dominant, with {210}, {10 $\bar{2}$ }, {001}, and {011}. As a crystallographically continuous, lamellar intergrowth with andryobertsite as plates, to 10 mm, that radiate from the center of an aggregate 1.4 cm long and 1 cm at the base.

**Physical Properties:** *Cleavage:* Good on (100). *Fracture:* Conchoidal. *Tenacity:* Brittle. Hardness = 3 D(meas.) = n.d. D(calc.) = 4.011

**Optical Properties:** Transparent. *Color:* Electric blue; greenish blue in transmitted light. *Streak:* Pale blue. *Luster:* Vitreous. *Optical Class:* Biaxial (-).  $\alpha = 1.713(3)$   $\beta = 1.743(1)$   $\gamma = 1.749(1)$   $2V(\text{meas.}) = 50(5)^\circ$   $2V(\text{calc.}) = 48^\circ$  *Orientation:*  $X \wedge a = 12^\circ$  (in  $\beta$  obtuse),  $Y = b$ ,  $Z = c$ . Nonpleochroic. *Dispersion:* Moderate,  $r < v$ , asymmetric.

**Cell Data:** *Space Group:*  $P2_1/m$ .  $a = 9.8102(9)$   $b = 10.0424(6)$   $c = 9.9788(7)$   $\beta = 101.686(7)^\circ$   $Z = 2$

**X-ray Powder Pattern:** Tsumeb mine, Namibia. 9.64 (100), 3.145 (50), 4.46 (40), 3.048 (40), 2.698 (40), 7.00 (30), 4.81 (30)

Chemistry	(1)
K <sub>2</sub> O	4.05
CaO	3.52
MnO	0.86
CdO	1.26
ZnO	0.04
CuO	32.86
As <sub>2</sub> O <sub>5</sub>	49.56
<u>H<sub>2</sub>O</u>	<u>[4.61]</u>
Total	96.75

(1) Tsumeb mine, Namibia; electron microprobe analysis supplemented by IR spectroscopy, H<sub>2</sub>O calculated from structure analysis; corresponds to  $K_{1.01}(Ca_{0.74}Cd_{0.12}Mn_{0.11})_{\Sigma=1.00}(Cu_{4.85}Zn_{0.01})_{\Sigma=4.86}(AsO_4)_{4.06}[As(OH)_2O_2](H_2O)_2$ .

**Occurrence:** On a single specimen from a weathered polymetallic mineral deposit.

**Association:** Cuprian adamite, zincian olivenite, andryobertsite, tennantite.

**Distribution:** From the Tsumeb mine, Namibia.

**Name:** The prefix, *calcio*, designates the calcium analog of *andryobertsite*.

**Type Material:** Royal Ontario Museum, Toronto, Canada (M47022 and M47110) and the Natural Museum of Natural History, Washington, D.C., USA (171487).

**References:** (1) Cooper, M.A., F.C. Hawthorne, W.W. Pinch, and J.D. Grice (1999) Andryobertsite and calcioandryobertsite: two new minerals from the Tsumeb mine, Tsumeb, Namibia. *Mineral. Record*, 30(3), 181-186. (2) (2000) *Amer. Mineral.*, 85, 1321 (abs. ref. 1). (3) Cooper, M.A. and F.C. Hawthorne (2000) Highly undersaturated anions in the crystal structure of andryobertsite – calcio-andryobertsite, a doubly acid arsenate of the form  $K(Cd,Ca)[Cu^{2+}_5(AsO_4)_4\{As(OH)_2O_2\}](H_2O)_2$ . *Can. Mineral.*, 38(4), 817-830.