

**Carraraite****Ca<sub>3</sub>Ge(SO<sub>4</sub>)(CO<sub>3</sub>)(OH)<sub>6</sub>•12H<sub>2</sub>O**

©2001-2005 Mineral Data Publishing, version 1

**Crystal Data:** Hexagonal. *Point Group:* 6/*m*. Hexagonal crystals, tabular on {0001}, to prismatic, elongated along [10 $\bar{1}$ 0], to 0.6 mm.

**Physical Properties:** Hardness = [2.5] (by analogy to the ettringite group).  
D(meas.) = n.d. D(calc.) = 1.979

**Optical Properties:** Transparent to translucent. *Color:* Milky white. *Luster:* Vitreous.  
*Optical Class:* Uniaxial (-)  $\omega = 1.509(1)$   $\epsilon = 1.479(1)$

**Cell Data:** *Space Group:* P6<sub>3</sub>/*m*.  $a = 11.056(3)$   $c = 10.629(6)$   $Z = 2$

**X-ray Powder Pattern:** Gioia quarry, Italy.  
9.57 (vs), 5.53 (s), 3.83 (s), 3.56 (ms), 2.74 (ms), 3.44 (m), 2.53 (m)

<b>Chemistry:</b>	(1)	(2)
SO <sub>3</sub>	16.19	12.00
CO <sub>2</sub>		6.60
GeO <sub>2</sub>	18.15	15.68
CaO	35.70	25.22
H <sub>2</sub> O		40.50
<u>Total</u>		<u>100.00</u>

(1) Gioia quarry, Italy; by electron microprobe, corresponds to Ca<sub>3</sub>Ge(SO<sub>4</sub>)<sub>1.08</sub>(CO<sub>3</sub>)<sub>0.92</sub>(OH)<sub>6</sub>•12H<sub>2</sub>O. (2) Ca<sub>3</sub>Ge(SO<sub>4</sub>)(CO<sub>3</sub>)(OH)<sub>6</sub>•12H<sub>2</sub>O as confirmed by crystal-structure analysis.

**Mineral Group:** Ettringite group.

**Occurrence:** A rare secondary mineral formed by late-stage hydrothermal alteration of earlier sulfides and sulfosalts.

**Association:** Nordstrandite, dawsonite.

**Distribution:** From the Gioia quarry, Colonnata Valley, northeast of Carrara, Tuscany, Italy.

**Name:** For its occurrence in the Carrara district, Italy.

**Type Material:** Natural History Museum, University of Pisa, Pisa, Italy.

**References:** (1) Merlino, S. and P. Orlandi (2001) Carraraite and zaccagnaites, two new minerals from the Carrara marble quarries: their chemical compositions, physical properties, and structural features. *Amer. Mineral.*, 86, 1293–1301.