


Qingheite



©2001-2005 Mineral Data Publishing, version 1

Crystal Data: Monoclinic. *Point Group:* $2/m$. Short prismatic to tabular anhedral grains, to 4 mm.

Physical Properties: *Cleavage:* On {010}, imperfect. *Fracture:* Conchoidal.
Tenacity: Brittle. Hardness = 5.3–5.6 $D(\text{meas.}) = 3.718$ $D(\text{calc.}) = 3.61$

Optical Properties: Semitransparent. *Color:* Jade-green to light yellowish green.
Luster: Vitreous.

Optical Class: Biaxial (+). *Pleochroism:* Strong; $X = \text{light yellowish green}$; $Y = \text{jade-green}$; $Z = \text{dark bluish green}$. *Dispersion:* $r \gg v$, strong. $\alpha = 1.678$ $\beta = 1.684$ $\gamma = 1.691$
 $2V(\text{meas.}) = 80^\circ$

Cell Data: *Space Group:* $P2_1/n$. $a = 11.856(3)$ $b = 12.411(3)$ $c = 6.421(1)$
 $\beta = 114.45(2)^\circ$ $Z = [4]$

X-ray Powder Pattern: Qinghe Co., China. (ICDD 41-1418).
2.685 (10), 3.472 (9), 2.512 (9), 6.21 (8), 2.860 (7), 1.739 (7), 3.082 (6)

Chemistry:

	(1)		(1)
P_2O_5	45.63	ZnO	0.23
TiO_2	0.05	MgO	9.75
Al_2O_3	4.53	CaO	0.93
Fe_2O_3	[2.24]	Li_2O	0.02
Cr_2O_3	0.04	Na_2O	8.73
FeO	[3.94]	K_2O	0.04
MnO	23.60	Total	[99.73]

(1) Qinghe Co., China; by electron microprobe, original total given as 99.72%, total Mn as MnO; with Fe partitioned to fill M2, corresponds to $\text{Na}_{1.31}(\text{Mn}_{1.50}\text{Mg}_{1.13}\text{Fe}_{0.27}^{2+}\text{Ca}_{0.08}\text{Zn}_{0.02})_{\Sigma=3.00}(\text{Al}_{0.42}\text{Fe}_{0.11}^{3+})_{\Sigma=0.53}(\text{PO}_4)_3$.

Occurrence: In a muscovite-rich pegmatite.

Association: Muscovite, quartz, microcline, braunite, pyrolusite.

Distribution: From an undisclosed locality in Qinghe Co., Xinjiang Uygur Autonomous Region, China.

Name: For Qinghe Co., China.

Type Material: n.d.

References: (1) Ma Zhesheng, Shi Nicheng, and Peng Zhizhong (1983) Crystal structure of a new phosphatic mineral – qingheite. *Scientia Sinica, Series B*, 26, 876–884 (in English). (2) (1984) *Amer. Mineral.*, 69, 567–568 (abs. ref. 1). (3) (1987) *Mineral. Abs.*, 38, 349 (abs. ref. 1).